



Product Code: E009-KIT

Manual Blaine Air Permeability Apparatus

Standard: AASHTO T153, BS 4359-2, EN 196-6, ASTM C204

Description:

This apparatus is used to determine the fineness of Portland cement in terms of the specific surface expressed as total surface area in square centimetres per gram of cement.

Technical Specifications

Measurement: Specific surface expressed as total surface area in square centimetres per gram of cement	Function: Determine the fineness of Portland cement
Coupling: Vaseline grease for better coupling tube/cell	Manometer: Glass U-tube manometer with valve
Dimensions: 220x180x470 mm	Weight: 12 Kg approx.
Filter Papers: 1000 filter paper disks included	Manometric Liquid: Included